



# TECHNICAL INFORMATION

## TIVAR<sup>®</sup> 88 AntiStatic

### Physical Properties

Property	Method	SI Unit	SI Value	English Unit	English Value
Density	ASTM D-792	kg/m <sup>3</sup>	946	lbs/ft <sup>3</sup>	59.01
Yield Point	ASTM D-638	MPa	21.9	psi	3176
Elongation at Yield	ASTM D-638	%	15	%	15
Tensile Break	ASTM D-638	MPa	33	psi	4786
Elongation at Break	ASTM D-638	%	192	%	200
Tensile Modulus	ASTM D-638	MPa	856	psi	124154
Flexural Modulus	ASTM D-790	MPa	772.1	psi	111985
Izod Impact	ASTM D-256A	J/m	No Break	Ft-lbs/in	No Break
Sand Wheel Wear	ASTM G-65,	T-1000=100	110	T-1000=100	110
Hardness	ASTM D-2240	Shore D	70	Shore D	70
Static Friction	ASTM D-1894	Unitless	0.20	Unitless	0.20
Dynamic Friction	ASTM D-1894	Unitless	0.14	Unitless	0.14
Coefficient of Thermal Exp.	ASTM D-696	<sup>o</sup> C <sup>-1</sup>	0.00018	<sup>o</sup> F <sup>-1</sup>	0.00011
Melt Point	ASTM D-3417	<sup>o</sup> C	137-143	<sup>o</sup> F	278-289
Compressive Modulus	ASTM D-695	MPa	na	psi	na
Compressive Deformation	ASTM D-621	% at 454.5 kg	4-6	% at 1000 psi	4-6
Volume Resistivity	ASTM D-257	Ohm-cm	10 <sup>5</sup> -10 <sup>9</sup>	Ohm-cm	10 <sup>5</sup> -10 <sup>9</sup>
Surface Resistivity	ASTM D-257	Ohm	10 <sup>5</sup> -10 <sup>9</sup>	Ohm	10 <sup>5</sup> -10 <sup>9</sup>
Water Absorption	ASTM D-570	%	nil	%	nil

\* Values are averages and are not specifications.

\*\* ASTM test methods are under current procedures.

**IMPORTANT:** Most plastics will ignite and sustain flame under certain conditions. Caution is urged where any material may be exposed to open flame or heat-generating equipment. Use Material Safety Data Sheets to determine auto-ignition and flashpoint temperatures of materials, or consult Poly Hi Solidur, Fort Wayne, Indiana if additional information is needed. The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Poly Hi Solidur, Inc. shall not be liable and the customer assumes all risk and liability of any use or handling of any material beyond Poly Hi Solidur's direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

TIVAR<sup>®</sup> is a registered trademark of Poly Hi Solidur, Inc.  
 ©2000 Poly Hi Solidur, Inc.  
 Form No T88AST

**POLY HI SOLIDUR**

A MENASHA SUBSIDIARY



2710 American Way, Fort Wayne, Indiana 46809  
 Telephone (219) 479-4100 FAX: (219) 478-1074

[www.polyhisolidur.com](http://www.polyhisolidur.com)